



American Gypsum
5960 Berkshire Ln., #800
Dallas, TX 75225
214-530-5500
www.americangypsum.com

Technical Information
1-800-545-6302 ext. 5607

Interior Ceiling Board

INTERIOR CEILING BOARD



Made in the USA



Panel de techo para interiores

| | |
|--|--|
| <p>DESCRIPTION</p> | <p>1/2" Interior Ceiling Board is specifically formulated to meet the need for a lower weight ceiling panel with increased integrity in its gypsum core, making its sag resistance equivalent to 5/8" Type X wallboard. American Gypsum's 1/2" Interior Ceiling Board is designed for use in wall and ceiling applications spaced no more than 24" o/c, and approved to be applied parallel or perpendicular to ceiling framing spaced up to 24" o/c, even when a hand applied or water-based texture is used for decoration.</p> <p>American Gypsum products contain no asbestos and no detectable levels of formaldehyde.</p> |
| <p>GREENGUARD CERTIFICATION FROM UL ENVIRONMENT</p> | <p>1/2" Interior Ceiling Board has achieved UL Environment's GREENGUARD GOLD Certification. GREENGUARD Certified products are scientifically proven to meet some of the world's most rigorous, third-party chemical emissions standards, helping reduce indoor air pollution and the risk of chemical exposure while aiding in the creation of healthier indoor environments. For more information, visit www.ul.com/gg.</p> |
| <p>BASIC USES</p> | <p>5/8" wallboard panels were once considered the best product for ceiling applications where the framing is spaced up to 24" o/c. However, product weight has always been a hindrance to proficient construction. The lighter weight 1/2" Interior Ceiling Board is specifically designed for interior ceilings in standard residential and commercial applications where framing members are spaced up to 24" o/c and a water-based texture will be used.</p> <p>The exceptional sag resistance of American Gypsum's Interior Ceiling Board has been independently verified by Progressive Engineering, Inc. when tested in accordance with ICC-ES AC417 (Acceptance Criteria for 1/2 Inch Sag-Resistant Gypsum Ceiling Board), and PEI Standard No. 94-9 - Large Scale Ceiling Board Load Test Procedure.</p> |
| <p>LIMITATIONS</p> | <p>1/2" Interior Ceiling Board is intended for interior applications only, do not use in exterior soffits or exterior ceiling applications.</p> <p>Avoid exposure to temperatures exceeding 125°F (52°C), e.g., located adjacent to wood burning stoves and or heating appliances.</p> <p>Avoid exposure to excessive or continuous moisture before, during and after installation, e.g., swimming pools, saunas or steam rooms. Eliminate any sources of moisture immediately.</p> <p>Gypsum panels are a nonstructural product and should not be used as a nailing base.</p> <p>Maximum span between ceiling framing members is 24" o/c.</p> <p>When 1/2" Interior Ceiling Board panels are used as a base for water-based texture finish, the weight of overlaid insulation shall not exceed 2.2 psf. Insulation blankets or batts should be recessed, with flanges attached or friction fitted to the sides of the studs or joists.</p> <p>If blown-in cellulose insulation is used, take care to follow insulation manufacturer's specifications on addition of water, as additional moisture in this insulation can cause excessive gypsum wallboard to sag.</p> <p>When a vapor retarder is installed on ceilings behind these ceiling panels, the ceiling insulation (batts or blankets) shall be installed before or immediately after the ceiling panels are installed. Where loose fill insulation is to be used above the ceiling, it shall be installed immediately after the ceiling panels are installed.</p> |
| <p>STORAGE AND HANDLING</p> | <p>Gypsum board does not generate or support the growth of mold when it is properly transported, stored, handled, installed, and maintained. However, mold spores are present everywhere and when conditions are favorable; mold can grow on practically any surface. GYPSUM BOARD MUST BE KEPT DRY to prevent the growth of mold.</p> <p>Gypsum board must be stored in an area that protects it from adverse weather conditions, condensation, and other forms of moisture. Job site conditions that can expose gypsum board to water or moisture must be avoided.</p> <p>Gypsum board must be protected during transit with a weather-tight cover in good condition. Plastic shipping bags are intended to provide protection during transit only and must be promptly removed upon arrival of the load. Failure to remove the shipping bag can increase the likelihood of developing conditions favorable to the growth of mold.</p> <p>Gypsum board that has visible mold growth must not be used. For additional information, refer to Gypsum Association publication, "Guidelines for the Prevention of Mold Growth on Gypsum Wallboard" (GA-238-03), which can be found at www.americangypsum.com under "Technical Data" - click on Gypsum Association Literature.</p> <p>Gypsum board must be stored off the ground and under protective cover. Sufficient risers must be used to assure support for the entire length of the wallboard to prevent sagging.</p> <p>Gypsum board must be delivered to the job site as near to the time it will be used as possible. Individuals delivering gypsum board to jobsites should ensure that it is carried, not dragged, to place of storage/installation to prevent damage to finished edges.</p> |

